

Appl. No. 09/936,538

Response dated November 12, 2004

Reply to Final Office Action dated August 25, 2004

IN THE CLAIMS

Claims 1-7 (Cancelled)

8. (Currently Amended) A damper comprising:
a hub;
an inertia mass body;
a polymer elastic body such a rubber press-fitted between the hub and the inertia mass body from an axis direction thereof, wherein said polymer elastic body is a vulcanized and molded rubber elastic body; and
an organosilane as a non-slip agent is provided at least one of between said hub formed by a metal member and said polymer elastic body and between said inertia mass body formed by a metal member and said polymer elastic body;
wherein surface roughness in at least one of a metal surface adhering to the polymer elastic body in said hub and a metal surface adhering to the polymer elastic body in said inertia mass body is within a range of [5] 15 to 50 μmRz (JIS B0601).

9. (Previously presented) The damper according to claim 8, wherein at least one of a metal surface adhering the polymer elastic body in said hub and a metal surface adhering to the polymer elastic body in said inertia mass body is without performing chemical surface treatment.

10. (Cancelled)

11. (Cancelled)

12. (Withdrawn) A process of a damper being a fitting type including a hub, a inertia mass body, and a polymer elastic body such a rubber press-fitted between the hub and the inertia mass body from an axis direction thereof, the process comprising:

a first step of applying an organosilane solution as a non-slip agent onto at least one of both surfaces of said hub and said inertia mass body, both surfaces facing the polymer elastic body;

Appl. No. 09/936,538

Response dated November 12, 2004

Reply to Final Office Action dated August 25, 2004

a second step of press-fitting the polymer elastic body applied onto the organosilane solution between the hub and the inertia mass body; and

a third step of heating the damper to remove a solvent thereof, reacting the organosilane in the surface of said polymer elastic body and at least one of both surface of said hub and said inertia mass body, and attaching and fitting said hub and said Inertia mass body.

13. (Withdrawn) A process of a damper being a fitting type including a hub, a inertia mass body, and a polymer elastic body such a rubber press-fitted between the hub and the inertia mass body from an axis direction thereof, the process comprising: a first step of applying an organosilane solution as a non-slip agent onto at least one of both surfaces of said hub and said Inertia mass body, said both surfaces being faced by respective surfaces of said polymer elastic body;

a second step of press-fitting said polymer elastic body between said hub and said inertia mass body after said first step; and

a third step of heating the damper to remove a solvent thereof, reacting the organosilane in the surface of said polymer elastic body and at least one of both surface of said hub and said inertia mass body, and attaching and fitting said hub and said inertia mass body.

14. (Withdrawn) The process of a damper according to claim 12, wherein at least one of both surfaces of said hub and said inertia mass body being attached and fitted to said organosilane, said both surfaces facing said polymer elastic body is without performing heat surface treatment.

15. (Withdrawn) The process of a damper according to claim 13, wherein at least one of both surfaces of said hub and said inertia mass body being attached and fitted to said organosilane, said both surfaces facing said polymer elastic body is without performing heat surface treatment.

16. (Withdrawn) The process of a damper according to claim 12, wherein surface roughness in at least of one of a metal surface adhering to the polymer elastic body in said hub and a metal surface adhering to the polymer elastic body in said inertia mass body is within a range of 5 to 50 μmRz (JISB0601).

Appl. No. 09/936,538

Response dated November 12, 2004

Reply to Final Office Action dated August 25, 2004

17. (Withdrawn) The process of a damper according to claim 13 wherein surface roughness in at least of one of a metal surface adhering to the polymer elastic body in said hub and a metal surface adhering to the polymer elastic body in said inertia mass body is within a range of 5 to 50 μmRz (JIS B0601).

18. (Withdrawn) The process of a damper according to claim 14, wherein surface roughness in at least of one of a metal surface adhering to the polymer elastic body in said hub and a metal surface adhering to the polymer elastic body in said inertia mass body is within a range of 5 to 50 μmRz (JIS B0601).

19. (Withdrawn) The process of a damper according to claim 15, wherein surface roughness in at least of one of a metal surface adhering the polymer elastic body in said hub and a metal surface adhering to the polymer elastic body in said inertia mass body is within a range of 5 to 50 μmRz (JIS B0601).